

**Test Report: (5119)337-0057 Revised2**
GALE PACIFIC USA, INC.

Received Date: December 03, 2019

Report Date: January 07, 2020

Revision Date: February 27, 2020

ADDITIONAL TEST RESULTS FOR GALE PACIFIC COMMERCIAL FABRICS**Standard Test Method for Surface Burning Characteristics of Building Materials**

Client Identification:	E: Yellow/Orange HDPE Yarn- E-Commercial Dualshade 350fr
Product Category:	Textile Type Product
Specimen Weight (lbs.):	3.2
Specimen Thickness (in.):	0.060
Adhesive:	No
Mounting:	Unadhered – sample not adhered to a substrate, instead it was laid over a 2" hexagonal wire mesh and ¼" rods
Length (ft.):	Three 8 ft. specimens butted end to end
Additional Observations:	Burning Drips to the floor considered to be moderate.

Results:	
Flame Spread Index (Rounded to nearest multiple of 5):	10
Smoke Developed*:	40
Time to Ignite (minutes:seconds):	00:11
Max Flame Spread Distance (ft.):	4.7
Max Flame Spread Time (sec.):	376
Class / Rating:	Class I or A rating

<u>Classification Criteria</u>	<u>Flame Spread Index</u>	<u>Smoke Developed</u>
Class I or A:	0 – 25	450 or less
Class II or B:	26 – 75	450 or less
Class III or C:	76 - 200	450 or less

<u>Overall Rating:</u>	Class I or A rating
-------------------------------	----------------------------

NT = Not Tested, as noncompliance was found with a previous set.

NR = Not Required to be tested.

M = Meets, NM = Not Meets

Notes:

* - If raw data is less than 200 result is rounded to the nearest multiple of 5. If raw data is 200 or more result is rounded to the nearest multiple of 50.